

REMOVING BLACK MAMBA FHG®

Removing Black Mamba FHG® becomes a straightforward process with the right approach. In this guide, we'll outline three different methods for safely and effectively removing Black Mamba FHG®, depending on its state: whether it's wet, partially cured, or fully cured.

Wet

If the adhesive is still wet, you can pry it off and remove the remaining Black Mamba FHGr® with acetone or denatured alcohol. Once the bonded item has been removed, both surfaces should be cleaned thoroughly to ensure there is no remaining Black Mamba before re-bonding.

Partially Cured

If the adhesive has been applied for less than 48 hours, you can use a razor knife and abrasives to gradually cut away the Black Mamba from the joint.

Cured

Black Mamba Adhesive never cures to a hard, brittle state. We recommend using an oscillating multi-tool with a very thin, fine blade to cut through the Black Mamba (which is like rubber when dry). Once the bonded item is removed, both surfaces should be cleaned thoroughly to ensure there is no remaining Black Mamba before re-bonding.

For more information, please contact:

support@mpi-matco.com

