

6015A SealFlex AC



Product Description

6015A SealFlex Acrylic Flashing Tape is a self-adhesive flashing membrane coated with a high-performance acrylic adhesive designed for sealing around windows, doors, and other openings and transitions in exterior walls. The product meets the requirements of AAMA 711-22. Custom colours, printing, and packaging may be available for private branding.

Features

- High-strength polyolefin film and acrylic adhesive seals around nails and helps prevent water intrusion
- Flexible film for ease of installation
- Conforms easily to inside and outside corners
- Puncture resistant
- UV resistant

Construction

Polyolefin film facer with acrylic adhesive on a PET liner.
Available in black, white, and custom facers in widths of 4 in, 6 in, 9 in, and 12 in.

Technical data

Property	Test Method	Typical Values	
		Imperial	Metric
Thickness w/o Liner	—	12 mil	305 µm
Tensile Breaking Strength	ASTM D3759	MD 24 lbf/in	MD 42 N/cm
Peel Adhesion: Stainless Steel	ASTM D3330-F	4.5 lbf/in	7.9 N/cm
Peel Adhesion: Plywood	ASTM D3330-F	5.2 lbf/in	9.1 N/cm
Peel Adhesion: OSB	ASTM D3330-F	3.3 lbf/in	5.7 N/cm
Peel Adhesion: Anodized Aluminum	ASTM D3330-F	6.0 lbf/in	10.5 N/cm
Peel Adhesion: PVC	ASTM D3330-F	4.6 lbf/in	8.1 N/cm
Peel Adhesion: Backing	ASTM D3330-F	5.8 lbf/in	10.2 N/cm
Nail Sealability	AAMA 711	Pass	



Additional Performance Data

Property	Test Method	Typical Values
Low Temperature Flexibility: 32°F (0°C)	ASTM C765	Pass
Accelerated UV Aging	AAMA 711 5.4	Pass
Elevated Temperature Exposure	AAMA 711 5.5	Pass - LV3
Thermal Cycling	AAMA 711 5.6	Pass
Water Immersion	AAMA 711 5.8	Pass
Resistance to Peel	AAMA 711 Annex A	Pass
Application Temperature, Minimum		30°F (-1°C)
Service Temperature		-40°F (-40°C)
Recommended Outdoor Exposure		90 Days

Storage & Usage Conditions

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight. Surfaces to which the tape is applied should be clean, dry, and free of grease, oil, and other contaminants.

Note: The physical and performance characteristics shown are averages obtained from tests performed in accordance with ASTM and PSTC test methods. MPI Matco makes no warranty of any kind, expressed or implied, as to the results of product use. The information provided herein is based on laboratory testing and is believed to be reliable. These values should not be used for specification purposes. Each user should conduct their own testing to determine the suitability of the product for their intended application and assumes all risks and liabilities in connection therewith. Materials should be stored at 70°F (21°C) and 50% relative humidity.

